

MITECH CORROSION RESISTANT CHARTS

K	A	Substantial resistance - Preferred material of construction	1	All figures given, unless otherwise specified are for normal temperatures and pressures
	B	Moderate Resistance - Satisfactory for use under most conditions: very slight swelling of elastomers	2	Applicable to the boiling point of the solution
E	C	Questionable Resistance - use with caution	3	Applicable up to 50° C
	D	Inadequate Resistance - Not Recommended	4	Air Free
Y			5	Subject to Pitting
	Blank	Insufficient Information Available	6	Ammonia free
			7	Ambient only

A	B	C	D	E	F	G	H	I	J	K	L	M	N	O	P	R	S	T	U	V	W	X	Y	Z
----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------	----------

Media	Cast Iron	Cast Steel	CF 8M	18Cr 10Ni 3Mo	Ferr- allium	EN 57	Alloy 20	Monel	Elitcto Less Nickel	Alloy 825	Hast B	Hast C	Alum Bronze	Al	Tita- nium	Bronze
-------	-----------	------------	-------	---------------	--------------	-------	----------	-------	---------------------	-----------	--------	--------	-------------	----	------------	--------

A																
Acetaldehyde	A	A	A	A		A	A	B	A	A		A	D	A	A	A
Acetate Solvents	A1	A1	A	A		A	A	A	A	A	A	A	A	A	A	A
Acetic Acid 10%	D	D	B	A2		A	A	A	A	A	A2/4	A	A1	A3	A	
Acetic Acid 60%	D	D	B	A		B	A	B	C	A	A2/4	A	A1	A3	A	D
Acetic Acid Glacial	D	D	B	A		C	A	B	C	A	A2	A	A1	A3	A	D
Acetic Acid Vapours	D	D	C	A		A	A	B	A			A	B	C		
Acetic Anhydride	D	D	B	A		B	A	B		A	B1	A2	B	A3	A	
Acetone	A	B5	A	A		A	A	A	A	A	A	A	A	A	A	A
Acetyl Chloride			A													
Acetylene	A	A	A	A		A	A	A	A	A	A	A	D	A		A
Acetamine	A		A					A								
Acrylonitrile	B	A	A	A		A	A	A		A	A	A	A	A	A	
Acrylonitrile	C	A	A				A	A								A
Adipic Acid 15-25%		D	A2	A2		A								A	A	
Alcohols	A	A	A	A		A	A	A	A	A	A	A	A	B	A	A
Aliphatic Esters	A	A	A	A		A	A	A	A	A	B	B	A	C	A	
Aliphatic Hydrocarbons	A	B	B	A		A	A	A	A	A	A	A	B	A	A	
Alkyl Chlorides (pure)	B	B	B5	A5	A	B5	A	A	A	A	A	B	A	C		
Aluminium	D	D	B	A	A	C	A	B	C	A		B	B	B5	A	
Aluminium Acetate							A									
Aluminium Chloride	D	D	C5	B5		C	A3	B	C	A3	A2	A	B	D	A3	D

MITECH CORROSION RESISTANT CHARTS

	A	B	C	D	E	F	G	H	I	J	K	L	M	N	O	P	R	S	T	U	V	W	X	Y	Z
F	Cast Iron	Cast Steel	CF 8M	18Cr 10Ni 3Mo	Ferr- alium	EN 57	Alloy 20	Monel	Elitcto Less Nickel	Alloy 825	Hast B	Hast C	Alum Bronze	Al	Tita- nium	Bronze									
Fatty Acids	D	D	B5	A		A	A	B	D	A	A	A	B	B	A	B									
Ferric Chloride	D	D	D	D	D	D	D	C	C	D	D	B	D	D	A	D									
Ferric Nitrate	D	D	B	A	A	B	A	D	D	A	C	A	D	D	A										
Ferric Sulphate	D	D	B2	A2	A2	A	A	D	D	A	D	A	D	D	A	C									
Ferrous Chloride		D	B													D									
Ferrous Sulphate	D	D	B5	B		B5	A	B	D	A	A	A2	B4	D	A										
Fertilizer Solution	A		A					A																	
Fish Oil	A		A					A																	
Flue Gas	A		A				A																		
Fluoride Salts	A		A																						
Fluorinated hydrocar. (freons)	B	B	B	B			B	A	B	B	A	A	B	B		B									
Fluorine (dry gas)	D	D	B	A		B	A	A	D	A	B	A	B	D	D	D									
Fluorine (wet gas)	D	D	D	D				A			B	A	D	D		D									
Fluosilicic Acid	D	D	C5	B		C5	B	B	D	B	A	A	D	D	D										
Formaldehyde - 40%	D	D	B	B		B	A	A	D	A	B	B	B	B	A	B									
Formic Acid < 50%	D	D	B5	A5	A	D	A	A	D	A	B	A	B4	C	C	C									
Formic Acid > 50%	D	D	C5	A5	A	D	B	A	D	A	B	A	B4	C	C	C									
Fruit Juices	D	D	A	A		A	A	B	D	A	A	A	B	B		B									
Fuel Oil	B	B	A	A		A	A	A	A	A	A	A	B	A	A										
Furfural	B3	C3	A2	A2		A	A	A	A	A	A	A	B	A	A	B									

MITECH CORROSION RESISTANT CHARTS

Sodium Hydroxide < 30%	B	B	A	A	A2	A	A2	A	A	A	A2	A2	B1	D	A	B
Sodium Hydroxide >30%	C	B	B	B	B	B	A1	A	B	A	A1	B	B	D	B	B
Sodium Hydrosulphide			A					A								
Sodium Hypochlorite	D	D	C5	C5	D	C5	C5	D	D	D	C	A	D	C	A	D
Sodium Metaphosphate	C	C	A	A		B	A	A	A	A	A	A	B	A	A	C
Sodium Metasilicate	B	B	A	A	A	B	A	A	B	A	A	A	B	A		
Sodium Nitrate	B	B	A2	A2		A	A	B	B	A		A	C	A	A	B
Sodium Nitrite	B	B	A2	A2	A	B	A	B	B	A		A	B	A	A	
Sodium Perborate	B	B	A	A		B	A	A	B	A	A2	A	B	A		C
Sodium Peroxide - 10%	D	D	A	A		B	A	A	C	A	A2	A2	D	D		C
Sodium Phosphate tribasic	C	B	B	B		B	A	A	A	A	A2	A	C	D	A	
Sodium Sulphate	B5	B	B	A		B	A	A	B	A	A2	A	B	B	A	
Sodium Sulphide	C	C	B5	B		B	A	B	C	A	A1	C	D	D	A	
Sodium Sulphite	B	B	A1	A1		B	A2	B	B	A		A	C	B	A	
Sodium Thiosulphate	D	D	A	A		B	A	B			A	A	B	A		D
Soyabean Oil	A		A	X				A								B
Stannic Chloride	D	D	C5	B5			B	C	D	B	B	A	D	D		
Stannous Chloride	D	D	C5	B5			A	C	D	B	B	A	D	D		
Starch	C	A	A	A	A	A	A	A	C	A	A	A	B	A	A	
Steam	B	B	A	A	A	A	A	A	A	A	A	A	B	A	A	B
Stearic Acid	C	B	A	A		B	A	C	B	A	A	A	C4	A	A	C
Styrene	A	A	A				A	A								A
Sulphamic Acid							A									
Sulphite Liquor			A													
Sugar Liquors	B	B	A	A		A	A	A	A	A	A	A	B	A	A	
Sulphonic Acids	D	D	B	B		B	B	X	B	A	B	A	X	C	B	
Sulphur (fused)	C	C	B5	A		B	A	A4	C	A	A	A	D	A	A	D
Sulphur Dioxide (dry)	C	B	A	A		A	B	B	D	B	B	A	B5	A	B	B
Sulphur Dioxide (wet)	D	D	C	B		C	B	D	D	B	C	A	D	B	B	
Sulphur Tioxide (dry)	A	A	A				A	A								A
Sulphuric Acid < 5%	D	D	C1	B3	A	D	A2	A4	D	A	A	A	C	C	B	D
Sulphuric Acid - 5-20%	D	D	D	C1	A	B2	A	A4	D	A	A	A	C4	D	C	D

